

Natural Stone is a relatively hard, naturally formed mineral or petrified matter, produced by nature. Therefore, considerable variations including, but not limited to, color, texture, size, and cleft will occur in all natural stone. Samples, sample panels, brochures, photographs, computer-generated pictures, and the Internet may be, in some measure, different from the stone you actually receive. Laboratory tests, if conducted, are performed on small samples and cannot be totally accurate because of the limited scale of the tests. Please be sure that all involved parties are aware of these facts, so an informed decision can be made regarding natural stone.

Use of Chemicals: Acid or chemical cleaners are not recommended because of the inability of the user to control its use, and are never recommended for Limestone and Marble. User accepts all risks.

DISCLAIMER OF WARRANTY AND DAMAGES:
 Rolling Rock Building Stone Inc. products are provided to you "AS IS" without warranty of any kind, either expressed or implied, including, but not limited to the implied warranties of merchantability, or fitness for a particular purpose.

Midnite™ Product Guide

Pattern Cut Pavers

Nominal Size Imperial, inch	Actual Size Metric, cm	Thickness Inches, (cm)	Average Pieces Per Crate	Approx. Weight Per Crate lbs.
12 x 12	30 x 30	1-3/16, (3cm)	128	2260
12 x 24	30 x 60		64	2260
18 x 18	45 x 45		64	2540
24 x 24	60 x 60		32	2260
24 x 36	60 x 90		32	3380
Mixed Sizes	8 pc. pattern		82 = 200SF	3520



Coping, Sills & Steps

	Actual Size (Imperial) Inch x feet-inch	Thickness (Inches)	Average Pieces Per Pallet	Approx. Weight Per Pallet (lbs.)
TV Sill	2.5 x 48	2	50	1240
Bull Nose	14 x 48	2	12	1660
Treads	12 x 48	2	12	1420
	14 x 48			1660
	18 x 48			2140
	24 x 48			2840
Heavy Steps	18 x 48	6	6	3170
	18 x 72		4	3170



Midnite™ Product Specifications

Geology: Basalt

Density ASTM C97: 175.8 lbs./ft³

Water Absorption ASTM C97: 0.32%

Compressive Strength ASTM C170:

Dry Parallel 24530 psi, Wet Parallel 27450 psi,

Dry Perpendicular 27700 psi, Wet Perpendicular 28680 psi

Modulus of Rupture ASTM C99: 3740 psi, dry, 3980 psi, wet

Product Type & Finish:

- **Pattern Cut Pavers:** Sawn 6 sides with thermal finish top.
- **Sill, Coping:** Sawn 6 sides with thermal finish top and rock-pitched face on 1 long edge. Bull nose (BN) is sawn 6 sides with thermal finish top and 1 long bull nose edge.
- **Heavy Steps:** Sawn 6 sides with thermal finish top and rock-pitched face on 1 long and 2 short edges.

Pattern Cut Size: Midnite™ Pavers are cut to near precise metric dimensions, producing a very high quality product having square corners. Imperial length and width measurements as indicated in inches reflect a nominal size which is approximately 1/2" short of the full dimension.

Special Notice on Pattern Size: This product is an *excellent* choice for dry-laid work due to the stone's uniform thickness & cut-to-square quality in addition to the ability to match pieces without extensive field cutting. (Example - Two 30 cm lengths = 60 cm.)

Custom: On larger projects with proper planning and advance notice we can order special sizes or custom fabricated material from the factory to meet job specific requirements in an effort to reduce on site time and labor and reduce overall project cost. Please consult a sales representative for more information.

