



Rolling Rock Building Stone, Inc., 40 Rolling Rock Road, Boyertown, PA 19512
 Phone: (610) 987-6226, Fax: (610) 987-9779, Web: www.rollrock.com

Natural Stone is a relatively hard, naturally formed mineral or petrified matter, produced by nature. Therefore, considerable variations including, but not limited to, color, texture, size, and cleft will occur in all natural stone. Samples, sample panels, brochures, photographs, computer-generated pictures, and the Internet may be, in some measure, different from the stone you actually receive. Laboratory tests, if conducted, are performed on small samples and cannot be totally accurate because of the limited scale of the tests. Please be sure that all involved parties are aware of these facts, so an informed decision can be made regarding natural stone.

Use of Chemicals: Acid or chemical cleaners are not recommended because of the inability of the user to control its use, and are never recommended for Limestone and Marble. User accepts all risks.

DISCLAIMER OF WARRANTY AND DAMAGES:

Rolling Rock Building Stone Inc. products are provided to you "AS IS" without warranty of any kind, either expressed or implied, including, but not limited to the implied warranties of merchantability, or fitness for a particular purpose.

Montauk Blue Product Guide

Pattern Cut Pavers

Nominal Size Imperial, (inch)	Actual Size Metric, (cm)	Thickness Inches, (cm)	Average Pieces Per Pallet	Approx. Weight Per Pallet (lbs.)
12 x 12	30 x 30	0.75-1, (2-2.5cm)	252	3150
12 x 18	30 x 45		152	2850
12 x 24	30 x 60		130	3250
12 x 36	30 x 90		90	3370
18 x 18	45 x 45		81	2280
18 x 24	45 x 60		78	2920
18 x 36	45 x 90		38	2140
24 x 24	60 x 60		43	2150
24 x 36	60 x 90		40	3000
36 x 36	90 x 90		40	4500
Mixed Sizes	8 pc. pattern		82 = 200SF	2500



Coping, Treads

14 x 48	1.5 (3.8cm)	20	1800
---------	-------------	----	------

Product ASTM

Geology: Slate

ASTM C121 Water Absorption : 0.28% average of six samples

ASTM C120 Modulus of Rupture: 7,154.4 psi average of six samples

ASTM C127 Weather Resistance of Slate: Depth of Softening (inches) 0.00, three samples

ASTM C-1028-96 Static Coefficient of Friction: Dry Test (.79 average) Wet Test (.64 Average)

Product Type & Finish

Pattern Cut Pavers: Natural cleft top & bottom with sawn edges.

Antique Accent Pavers: Smooth tumbled finish (check availability).

Coping/Tread: Natural Cleft top, calibrated thickness, full bull nose one long edge, sawn ends & back.

Product Notes

Thickness: Pattern Cut Pavers: ¾" to 1"

Pattern Cut Sizes: Measurements indicated in inches reflect a nominal size, short of the Imperial size. Montauk Pavers are actually cut on a tile line to precise metric dimensions allowing for the production of a very high quality product having square corners.

Custom: On larger projects with proper planning and advance notice we can order special sizes or custom fabricated material from the factory to meet job specific requirement. This will reduce time and labor on site and may reduce overall project cost. Please consult a sales representative for more information.

